

## S 28 F

**1) Product Description :** The grade is for the production of biaxially oriented poly propylene films and is particularly suitable for metallization .

**2) Applications :**

- Cosmetics , food stuffs , lamination and other flexible films .

**3) Typical data**

Property	Unit	Typical Value	Test Method
M.F.I	Dg/min	2	ISO 1133
Density	g/cm <sup>3</sup>	0.9	ISO 1183
Flexural Modulus	N/mm <sup>2</sup>	1450	ISO 178
Tensile	N/mm <sup>2</sup>	35	ISO R527
Elongation	%	13	ISO R527
Izod Impact	Kj/m <sup>2</sup>	6.5	ISO 180
Hardness	point	71	ISO 868
Vicat	°C	155	ISO 306/A
H.D.T	°C	105	ISO 75/B

\* Typical Values : not to be construed as specifications

Producer: Marun Petrochemical Co.

Licensor: Basell

Packing: 25 Kg plastic bag